## **Finishing**

CLIENT

## **Automotive**



ARTICLE **MUSTANG ORIENTED - GRIP** BASED ON WE RECIPE NO.

MATERIAL Wet White - FG Grain DATE

COLOUR DESIGN COLLECTION - MORGANITE TECHNICIAN Automotive Competence Team

Product	1	2	3	4	5	6	Procedure
RODA® Car P mix	150	70					Basecoat:
RODA® Car B 34 /N	785						1) 1x Mega Star 11-12 gr/sqft
BAYDERM® Bottom CTR	50						1
RODA® Link 5777	15						Rest overnight
RODA® Wax 4001		300					Emboss: "Corazon"
RODA® Base AF-B		100					1
Water		100	185				Mill:
RODA® Car Dull 92/N			320				2 hours
BAYDERM® Bottom DLV-N			45				
AQUADERM® Finish HW-2			45				2) Effect coat: visc. 28-30" FC 4
AQUADERM® Additive GF			35				2x Mega Star 30G roller 1,0-1,1 g/sqft each
ROSILK™ 2229 FM			15				
RODA® Feel N 4			40				Dry mill 1 h - Light stake
RODA® Tec AW			90				Iron "Sandblast": 125°C, 6 m/min, 30 bar
RODA® Fix 6271/D			140				1
AQUADERM® Fluid H			15				3) Top coat:
AQUADERM® XL DI 2			70				2x spray 2-3 g/sqft each
VISC. DIN Cup 4mm	50-55"	28"-30"	26"-28"				
							_
Total	1000	570	1000	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.