Finishing

CLIENT

Automotive



ARTICLE SHANGHAI REVIVAL - METALLIC BASED ON WE RECIPE NO.

MATERIAL Wet blue - FG Grain DATE

COLOUR DESIGN COLLECTION - DIVA BLUE TECHNICIAN Automotive Competence Team

Product	1	2	3	4	5	6	Procedure
AQUADERM® FLUID E EXP 2270	10						made by release paper "Komet UM 38"
AQUADERM® Finish HAT/N	580						1
BAYDERM® Bottom DLV-N	250						1) Preskin by reverse coat
RODA® Poliperl Iridescent Blue	40						on release paper (2-3-gr.sqft)
AQUADERM® XL 50	40						1
RODA® Car Pigment Mix	80						2) Adhesive by reverse coat
ACRYSOL™ RM 819W Rheol. Mod.	Х						on leather (8-10gr.sqft)
RODA® Line IC		690					
Water		170					
AQUADERM®Fluid E EXP 2270		10					
RODA® Car Pigment Mix		85					7
AQUADERM® XL 50		45					1
ACRYSOL™ RM 819W Rheol. Mod.		х					7
							7
							7
VISC. DIN Cup 4	45"	35"					
							_
							_
							_
					<u> </u>		4
							4
							4
							4
				<u> </u>	<u> </u>	<u> </u>	_
Total	1000	1000	0	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

