Finishing

CLIENT

Automotive



ARTICLE SHANGHAI REVIVAL - JEANS BASED ON WE RECIPE NO.

MATERIAL Wet blue - FG Grain DATE

COLOUR DESIGN COLLECTION - DIVA BLUE TECHNICIAN Automotive Competence Team

Product	1	2	3	4	5	6	Procedure
AQUADERM® FLUID E EXP 2270	10						on release paper "Komet UM54"
AQUADERM® Finish HAT/N	580						
BAYDERM® Bottom DLV-N	250						
RODA® Poliperl Iridescent Blue	40						1) Preskin by reverse coat
RODA® Car Blue SP/NP	80						on release paper (2-3-gr.sqft)
ACRYSOL™ RM 819W Rheol. Mod.	Х						
AQUADERM® XL 50	40						2) Adhesive by reverse coat
RODA® Line IC		690					on leather (8-10gr.sqft)
Water		170					
AQUADERM®Fluid E EXP 2270		10					
RODA® Car Pigment Mix		85					7
AQUADERM® XL 50		45					
ACRYSOL™ RM 819W Rheol. Mod.		Х					
RODA Car Pigment Mix							1
RODA® Car White P			961				
RODA® Car Violet P			4				7
RODA® Car Ochre P			6				7
RODA® Car Lemon P			16				
RODA® Car Brown P			12				
RODA® Car Blue SP/NP			1				
VISC. DIN Cup 4	45"	35"					
·]
							1
]
							1
]
							-
							1
Total	1000	1000	1000	0	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.