Finishing

CLIENT

Automotive

RECIPE NO. Nr. 12

ARTICLE STRAVINSKY ACADEMY - VEGETAL BASED ON WE RECIPE NO.

MATERIAL X-Tan - Veg. Retanning - FG Grain DATE

COLOUR DESIGN COLLECTION - SUN BAKED TECHNICIAN Automotive Competence Team

Product	1	2	3	4	5	6	Procedure
AQUADERM® FLUID H	5						Release paper Komet DE169
RODA® Car Pigment Mix	60						_
RODA® Line SLG	300						1) Preskin by reverse coat
BAYDERM® Bottom DLV-N	200						on release paper (2-3-g/sqft)
AQUADERM® Finish HW2/N	435						
ACRYSOL™ RM 819W Rheol. Mod.	х						2) Skin by reverse coat
RODA® Car Pigment Mix		90					on release paper (2-3 g/sqft)
EUDERM® Matt SN 2		70					
RODA® Line IC		280					3)Adhesive by reverse coat
Bayderm [®] Bottom DLV-N		550					on leather (8-10 g/sqft)
AQUADERM® Fluid H		10					
ACRYSOL™ RM 819W Rheol. Mod.		х					
RODA® Line AS			600				
PRIMAL™ FGR Emulsion			260				
AQUADERM® Fluid H			10				
RODA® Car Pigment Mix			90				
AQUADERM® XL 50			40				
ACRYSOL™ RM 819W Rheol. Mod.			Х				
							After Green Finishing
Water				530	170		4) Effect coat:
RODA® Wax 4001				300			2x light spray coats 1,5 g/sqft each
RODA® Base AF-B/N				100			
RODA® Car Pigment Mix				70			Rest for 6 hours
RODA® Fix 5792/N2					520		
AQUADERM® Matt HPM-N					90		Dry mill 40-50 min (to effect)
BAYDERM® Bottom DLV-N					45		
AQUADERM® Finish HW2/N					45		Sandblast 125°C, 50 bar, 7 m/min
AQUADERM® Fluid H					10		
ROSILK™ 2229 Feel Modifier					20		5) Top coat :
RODA® Feel N 4					50		2x spray coats 2,5 g/sqft each
ACRYSOL™ RM 819W Rheol. Mod.					Х		
AQUADERM® XL DI 2					50		4
VISC. DIN Cup 4	45-50"	45"	35"	15"	26-28"		1
Total	1000	1000	1000	1000	1000	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.