



# WET-END

## Retanning - dyeing

<b>ARTICLE</b>	Stravinsky Academy	<b>TA NUMBER</b>	
<b>MATERIAL</b>	X-white German Bulls	<b>DATE</b>	
	Shaved weight	<b>COLOUR</b>	Sun baked

Process	%		Time		
<b>Wash</b>	200	Water 35°C			
	1	CORIPOL® TR			
	1	CORIPOL® SG	45'		pH 5.20
<b>Drain</b>					
<b>Neutralisation</b>	150	Water 30°C			
	3	BAYKANOL® RFS Liq	20'		
+	2	TANIGAN® PAK-S			
	1.5	Sodium formate	30'		
+	1	Sodium bicarbonate	60'		pH 6.50
<b>Drain</b>					
<b>Wash</b>	200	Water 35°C	10'		
<b>Drain</b>					
<b>Retan</b>	100	Water 35°C			
	2	CORIPOL® SG			
	2	CORIPOL® AT			
	5	BAYKANOL® RFS Liq	20'		
+	3	RETINGAN® Pure RS			
	7	TANIGAN® BNO liq			
	5	Mimosa			
	5	Tara	30'		
+	7	TANIGAN® BNO liq			
	5	Mimosa			
	5	Tara	30'		
+	2	BAYKANOL® SL			
	2	TANIGAN® PR			
	1.3	SELLA® FAST BROWN EGR			
	0.4	SELLA® FAST YELLOW 4GL	90'		
+	100	Water 50°C			
	6	CORIPOL® AT			

TRADEMARK® and TRADEMARK® are in registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



## WET-END

### Retanning - dyeing

<b>ARTICLE</b>	Stravinsky Academy	<b>TA NUMBER</b>	
<b>MATERIAL</b>	X-white German Bulls	<b>DATE</b>	
	Shaved weight	<b>COLOUR</b>	Sun baked

	1	RODA® OIL 1449			
	4	CORIPOL® SG	40'		
+	3	MAGNOPAL® Pure B	40'		
+	1.5	Formic acid 85%	20'		pH 4.00
+	1.5	Formic acid 85%	40'		pH 3.70
<b>Drain</b>					
	200	Water 30°C			
	0.5	Oxalic acid			
	2	BORRON® LB	30'		
<b>Drain</b>					

**SET OUT– VACUUM DRY 45°C 240 sec – HANG TILL DRY – Stake 5-5-6-6**

TRADEMARK® and TRADEMARK® are in registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.