## **Finishing**

## **Shoe Upper**

CLIENT TFL RECIPE NO. BU 6176

ARTICLE N°10 SAMURAI BASED ON WE RECIPE NO.

MATERIAL **GOAT SKIN C.G.** DATE **MARCH 24**COLOUR **OFF WHITE** TECHNICIAN **Borgia Roberto** 

Product	1	2	3	4	5	6	Procedure
RODA®Lite 07 MIX	60	50		i !	<u> </u>	ļ	BUFFING GRAIN BEFORE FINISHING
EUDERM® X GRADE MP 2/N	800			<u> </u>	l	†	_i
RODA® Base WH 0303/N	200	250		İ	i	†	1) 1X ROLLER G25G
RODA®Link PAX	10			¦	<u> </u>	†	IRON 120°C - 50 Kg
WATER		250	200	200		1	
RODA® Lac CAB Dull/N			100			1	2) 2X SPRAY
RODA® Fix 6271/B				200	 	1	
AQUADERM® XL 71				7			3) 1X SPRAY
AQUADERM® X Shield LS/N				3	[	T	DRY MILL TO EFFECT
	Ī			İ	<u> </u>	Ī	
				İ	<u> </u>	T	4) 2X SPRAY
				 		1	IRON 90°C - 50Kg
				!	   	1	DRY MILL TO EFFECT
				 	}	1	
				! !			
	Ť			† !	 	1	
				! !	 	1	
				i	 	1	
				!		1	
				İ		1	
				ļ	 	1	
				İ		1	
	1			! !	 	1	
				i	i	İ	
				<del> </del>		†	
	<u> </u>			i	i	†	
						†	
				ļ	ļ	†	
				!		†	
	- <del> </del>			ļ	ļ	†	
	Ť			<del> </del>	i	†	
				} !		<del> </del>	
				<del> </del>	 	<del> </del>	
						<del> </del>	
Total	1070	550	300	410	0	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

