Finishing

TFL

CLIENT



RECIPE NO. BU 6383

ARTICLE N°13 ROSE' BASED ON WE RECIPE NO.

MATERIAL COW SIDE C.G. DATE Febr. 25

COLOUR TPX 15-1512 TECHNICIAN Borgia Roberto

RODA® Penetrator IE 880/N2	{						· ·
	100	50		 			!
EUDERM® Prebottom VE-N	100						1) 1X ROLLER 20B - 38gr.sqft
WATER	200	650					REST OVER NIGHT - VACUUM 60°C - 3"
PRIMAL™ FGR		300					REBUFF 400 PAPER
RODA® Lite 07 MIX			150				
RODA® Car B 35			650	650			2) 1X ROLLER 30A 20gr.sqft
RODA® Link PAX			30	30	20		REST OVER NIGHT - VACUUM 60°C
RODA® Cryl 5416			100	100			BUFFED 400 PAPER
PRIMAL™ SCL-371			100	100			
EUDERM® Nappa Soft S-C			50	50			3) 2X ROLLER G25G
RODA® Fix 5040 Dull					300		IRON 90°C - 100Kg
AQUADERM® Finish HAT					500		+ 2X ROLLER G25G
AQUADERM® Fluid H			10	10	10		7 1
RODA® Polipearl Iride RED				10			4) 2X ROLLER 30C
SELLA® Derm M2 Mix				Х			
AQUADERM® Additive DF					5		5) 2X ROLLER 30C
Total	400	1000	1090	950	835	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

