

Leather Goods

CLIENT	TFL
ARTICLE	N°23 GOLDEN
MATERIAL	HALF CALFC F.G.
COLOUR	TPX 17-1046

RECIPE NO.
BASED ON WE RECIPE NO.
DATE
TECHNICIAN

Product	1	2	3	4	5	6	Procedure
RODA® Wax 1423	100						
Water	100	200	550	100	100	200	1) 1X SP
RODA®Pur ADX		100					IRONIN
IPA		200					EMBOS
RODA® Cor HTP Mix			20				2) 1X SI
RODA®Bind TLC 385			150	30	30		
AQUADERM® Pure Finish 1813			50				3) 3X SP
RODA®Cryl NP 87			150				
AQUADERM® Pure Finish 5427			100	100	100		4) 2X S
AQUADERM® X-Biomer® XL 7010					5		
AQUADERM® Additive XF					3		5) 2X S
RODA®Wax SCH/N						10	IRONIN
RODA®Wax 4077/N						20	
RODA®Wax 4053						20	6) 1X SI
SELLA® Derm M2 Mix				10			STACKIN IRONIN
Total	200	500	1020	240	238	250	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing the correct application of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the responsibility of the customer. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



MEMA 25009

27 February 2025
Maurizio Menichetti

ire

'RAY

G Roto 110°C - 30 atm

S "Gaudi" Stampe & Stampe

P'RAY

'RAY

.PRAY

.PRAY

G roto 110°C - 30atm

P'RAY

IG

G Roto 120°C - 15 atm

ng his own tests to determine the suitability of the
customer's sphere of responsibility.