

Finishing Shoe Upper

CLIENT	TFL
ARTICLE	N° 24 BUTLER
MATERIAL	Half cow
COLOUR	TPX 181415

RECIPE NO.
BASED ON WE RECIPE NO.
DATE
TECHNICIAN

Product	1	2	3	4	5	6	Procedure
RODA® Pure OIL AA 4040	500	20					1) 1X R about 6 Milling
Water	500	450		400	400		
RODA® Wax 944		30					2) 2X Sp Sandbla
RODA® Pure Prebase 772/HD		100					
RODA® Bind TLC 327		50		50			
RODA® Cryl NP 87		100		120			
RODA® Lac 1028			500				3) Tippi
RODA® Pure Luster 1505				50	50		4) 3X Sp
RODA® Pur 5427/N				30			5) 2X Sp
RODA® Pur 64/N				20			
RODA® Link 5777				5			Ironing
SELLA® Derm M2 Mix			50	15			
RODA® Wax KCF 699					30		
RODA® Pure Luster 682					50		
RODA® Pur 5329/N Conc					150		
RODA® Feel N4					5		
RODA® Pur 5008					20		
RODA® Link 4009					20		
RODA® Link PAX					3		
Total	1000	750	550	690	728	0	

Comments:

* Mix well together

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from per supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes with We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

performing his own tests to determine the suitability of the in the customer's sphere of responsibility.