Finishing

CLIENT

Leather Goods

TFL

RECIPE NO. BU 6360

ARTICLE N° 27 AGATE BASED ON WE RECIPE NO.

MATERIAL 1/2 Bovine full grain DATE 13 January 2025
COLOUR 15-6307 TECHNICIAN Giorgio Giraudo

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 mix	70	70	15				1) 2 reverse coat,(cylinder 30 C), dry
RODA® Ground 1401	400						embossed hair cell 100°C at 150 bar,
RODA® Base AF-B/N	400						dry drum 8 hrs,
BAYDERM® Bottom 10UD	80	100					
EUDERM® X Grade SF	50						2) 2 spray coat, dry ,ironing 90°C at 50 bar
Water		440	500				2 spray coat, dry
RODA®Pure Luster 1430		80					
EUDERM® Wax CL-C		30			İ	<u> </u>	İ
RODA® Wax KCF 616		30					3) 2 spray coats, dry, ironing 90°C at 50 bar
RODA® Pur WX 1418/F		70	70				dry drum 2 hrs, vacuum
RODA® Pur 5427/N		50	100				
EUDERM® Dispersion MA		100					
RODA® Feel KTA 950		20			 		
RODA® Wax KCF 699			60		 		
RODA® Pure Luster 1505			150				
AQUADERM®Finish HAT/N			60				
RODA®Feel Microsil			20				
RODA®Link PAX		10	20				
Luxan C001 (Eckart)			5				
Total	1000	1000	1000	0	0	0	
Comments	1000	1000	1000	J	J	U	1

Comments:

 RODA^{\otimes} is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery

