## **Finishing**

## **Leather Goods**

CLIENT TFL RECIPE NO. BU 6369

ARTICLE N° 28 FINT GRAY BASED ON WE RECIPE NO.

MATERIAL Cow Side DATE 22 January 2025 COLOUR TPX 16-5803 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Penetrator IE880/N2	100	   	   	I     		 	1) 1X ROLLER G25G - 18gr.sqft
Water	200	! !	400	200		 	REST OVER NIGHT
PRIMAL™ FGR	100		 	 			VACUUM 70°C -2'
RODA® Lite 07 MIX	Ţ	70		 			
RODA® Pure Prebase 772/HD		100					2) 1X ROLLER 30C
RODA® Care NL	Ţ	100		 		 	SANDBLAST 90°C - 30 atm
RODA® Pur WX 1418/F		100		 			 
SELLA® Derm PINK M2			1				3) 4X SPRAY
RODA® Wax KCF 638			30				
PRIMAL™ SB 150			100				4) 2X SPRAY
RODA® Pur 5302/N		[	120	[		[	IRON 110°C - 70 Kg
RODA® Bind TLC 385		 	50	50			
RODA® Fix 5188/N Gloss				150		[	]
AQUADERM® Additive DF				2		<u> </u>	 
RODA® Wax KCF 699				30		] 	
RODA® Link PAX			8	3			
RODA® Polipearl IRIDE			5				
RODA® Polipearl IRIDE RED			5				
				ļ 		 	
		 	: 	: 			
		i 	ļ 	ļ 		ļ 	i 
				ļ		ļ	
						ļ	
						ļ	
						ļ	
		i 		i 		ļ	i
				ļ		ļ	
	. <del> </del>	<u> </u>	ļ	ļ		ļ	1
		ļ				ļ	
		<u> </u>		ļ 		ļ	i 
		<u> </u>		ļ		ļ	
		i !		ļ		ļ	İ
				ļ		<u> </u>	
	- <del> </del>	i I		ļ		ļ	i
Total	400	370	719	435	0	0	
0	-						<u> </u>

## Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

<sup>\*</sup> Mix well together