Finishing

CLIENT

Shoe Upper

RECIPE NO. BU 6349

ARTICLE N°29 CHARCOAL BASED ON WE RECIPE NO.

MATERIAL LAMB SKIN DATE 10 March 2025
COLOUR TPX 18-0601 TECHNICIAN TIRELLI GIANCARLO

					6	Procedure
600	600	500			ļ	1) 2X SPRAY
240				1	 	ROTOPRESS 100° C/ 50 ATM
90						
70	100				ļ	2) 2X SPRAY
	70					HAIRCELL 110° C/ 30 ATM
	40			i	 	+6X SPRAY
	50				<u> </u>	
	60					3) 2X SPRAY
	60					ROTOPRESS 100° C/ 20 ATM
	20					
		400			[
		100		Ī	 	
		10			<u> </u>	
		10			 	
		20				
		5				
		5				
					ļ	
					ļ	
					i 	
				ļ	ļ	
				ļ	ļ	
				ļ	ļ	
.i				ļ	i 	i
					ļ 	
.j				ļ	ļ	i
				ļ	ļ	
				ļ	ļ	<u> </u>
					<u> </u>	
1000	1000	1050	0	0	0	
	240	240 90 70 100 70 40 50 60 20	240 90 70 100 70 40 50 60 60 20 400 100 10 20 5 5	240 90 70 100 70 40 50 60 20 400 100 10 10 20 5 5	240 90 70 100 70 40 50 60 20 400 100 10 10 20 5	240 90 70 100 70 40 50 60 60 20 100 10 20 5 5

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.