

## Finishing Shoe Upper

CLIENT	TFL
ARTICLE	N°31 ROSSMORE
MATERIAL	Half cow
COLOUR	TPX 191758

RECIPE NO.  
BASED ON WE RECIPE NO.  
DATE  
TECHNICIAN

Product	1	2	3	4	5	6	Procedure
RODA® Ground 1401	500						1) 2X To
RODA® Pure Prebase 772/HD	200						FC6 20"
EUDERM® Prebottom RP-N-A	100						
RODA® Lite 07 Mix	100						2) 1X Sp Emboss
RODA® Lac WR		100					
Water		100	200	100			3) 3X Sp
RODA® Pur W 1813/N2			200				
RODA® Fix 5040 Dull			50				4) 2X Sp
RODA® Wax PUR			200				Plate 9C
SELLA® Derm M2 Mix			15				
RODA® Link PAX			6	2			5) 3X TI
RODA® Fix 1000				100			Ironing Milling &
RODA® Pur 5805/N3					1000		Stacking
Total	900	200	671	202	1000	0	

**Comments:**

\* Mix well together

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from per supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes with We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.



**MEMA 25002**

**23 January 2025**

**Maurizio Menichetti**

---

**ire**

---

ip star R2.5  
about 2g/Sf

ray  
Palmellato

ray

ray  
l°C 50 atm

**PPING ROLLER 500L**

90°C 20Atm  
2h

3

forming his own tests to determine the suitability of the  
in the customer's sphere of responsibility.