Finishing

CLIENT

ARTICLE

Leather Goods

RECIPE NO. BU 6348

N°8 BLUE ORIZON BASED ON WE RECIPE NO.

MATERIAL SHEEP SKIN DATE 01 March 2025
COLOUR TPX 18-3929 TECHNICIAN TIRELLI GIANCARLO

Product	1	2	3	4	5	6	Procedure
l WATER	200	500	550	500		 	1) 2 X SPRAY
RODA® Pur 5101/N	500					L	REST OVER NIGHT
RODA® Pure Oil AA 4040	300						ROTOPRESS 120° C/20 ATM
METOXYPROPANOL		250	50				
RODA® Pur ADX		250					2) 1X SPRAY
RODA® Cryl 114			80			 	
PRIMAL™ FGR			70			L	3) 4X SPRAY
RODA® Pur W 1817			50				ROTOPRESS 100° C/ 30 ATM
RODA® Pur EP19/F			100				+4X SPRAY
RODA® Wax 944			80				
RODA® Pure Luster 1430			70				4) 2X SPRAY
RODA® Casi MIX			80				CARTEGGIARE 130° C/ 40 atm
AQUADERM® XL 71			10			j	
RODA® Pur W1813/N2				350		 	EMBOSS "LUNARE" + "RAGGIO DI SOLE"
RODA® Pur 5329/N CONC.				130			MILLING 3h
RODA® Wax KCF 699				20			ROTOPRESS 120° C/ 5 ATM
RODA® Link PAX				20			MILLING 10 min
RODA® Feel N4				10			
RODA® Feel S5796				10			
						i 	
			 			ļ 	
						ļ	
						<u> </u>	
						i 	
						ļ	
				ļi		ļ	
						ļ	
						ļ	
						ļ	
Total	1000	1000	1140	1040	0	0	
i otai	1000	1000	1140	1040	U	U	1

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.