

Wet End - Process Formulation (RETAN)



N25 BRANDY wet end.xlsx

Date: 21-Jan-2025

Technician:

Company: FASHION A/W 26-27

Type of Leather: Shoe Upper & Leather Goods

Trial - N°:

Aim of Trial: art 25 BRANDY

Color: 17-1046

Project - N°:

Piece count:

Material: calf wb 牛皮藍皮

Substance: 1,6/1,7 mm

% refer to: Shaved削匀重

Weight:

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300,00	0,000	Water水	40°C			
		0,50	0,000	Formic acid甲酸				
		0,30	0,000	BORRON® ADN			30'	drain控水
			0,000					
		100,00	0,000	Water水	40°C			
		0,50	0,000	CORIPOL® SG				
		3,00	0,000	SELLASOL® PURE M			30'	
		5,00	0,000	TANNESCO® HN gran.			60'	
		1,00	0,000	sodium formate甲酸钠			120'	automatic overnight自动过夜
			0,000					morning pH=3,8 drain次日控水
		150,00	0,000	Water水	30°C			
		3,00	0,000	SELLASOL® NG LIQ				
		1,00	0,000	sodium formate甲酸钠			30'	
		0,50	0,000	sodium bicarbonate小苏打				
		4,00	0,000	MAGNOPAL® PURE B			40'	pH=4,8/5 drain,wash控水水洗
			0,000					
		80,00	0,000	Water水	30°C			
		3,00	0,000	RETINGAN® PURE RS			20'	
		0,50	0,000	CORIPOL® BZE-N			10'	
		5,00	0,000	TANIGAN® PURE T-A				
		5,00	0,000	mimosa				
		3,00	0,000	SELLASOL® PURE M			30'	
		4,00	0,000	MAGNOPAL® PURE B			60'	
		100,00	0,000	Water水	50°C			
		0,50	0,000	Formic acid甲酸			30'	drain, wash控水水洗
			0,000					
		100,00		Water水	50°C			
		3,00	0,000	CORIPOL® PURE LC-A				
		3,00	0,000	CORIPOL® PURE V				
		0,50	0,000	BORRON® SAF-A			60'	
		2,00	0,000	MAGNOPAL® PURE A			30'	
		0,50	0,000	Formic acid甲酸			30'	drain 控水

Mechanical Operation:

set out vacuum 250" 40°C

伸展，真空干燥250" 40°C

Process Information:

Running Time: 0 hrs 0 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery. Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..