## **Finishing**



CLIENTIILF 24RECIPE NO.IILF 2411ARTICLESTANCHBASED ON WE RECIPE NO.ACI23514WEMATERIALSHEEP FGDATE21 December 2023

COLOUR BAJA BLUE (TPX 18-3946) TECHNICIAN SANKARALINGAM

Product	1	2	3	4	5	6	7	Procedure
RODA® Base K 5025/FN	50							1) 3 X Spray
RODA® Wax K 619	50				1		I	Iron@ 80°C/40 pressure
RODA® Pur K 8727	75							
RODA® Bind K 4080	50							2) 4 X Spray
RODA® Ground KCF 647	50				į.			
RODA® Wax KCF 638	50	40						3) 2 X Spray
RODA® Feel KTA 950	20							Iron@ 90°C/40 pressure
AQUADERM® X-Shield HO	40	50	50					
RODA® KP Mix	75							
RODA® Cryl 744		50						
RODA® Base AF-B/N		100						
RODA® Pur EP 8		75						
PRODUCT WX 5266		50						
RODA® Cryl NP 86		50						
RODA® Lite 07 Mix		100			T	-		
AQUADERM® Additive XF	1	10	20	( !				
WATER	600	550	500	!	†	<u> </u>	İ	
RODA® Fix 6271/B		  -	250	 		!	†	!
RODA® Fix 5188/N Gloss	<del>-</del>	i	250		†	i	İ	
RODA® Link C 70			20				i	
	+	}		İ	†		İ	
		ļ			ļ		ļ	
	<del>i</del>	ļ	<u>.</u>		<del>-</del>	<del></del>	<del>-</del>	
		ļ			<u> </u>	ļ	ļ	
		ļ	i 		ļ	ļ	ļ	<u> </u>
					ļ		ļ	
		ļ	i 		ļ	ļ	ļ 	
		 			ļ	ļ	ļ	
		<u> </u>	! !	! !	<u> </u>	<u> </u>	1	 
		L			1			
		[			I			
	T.	[	[		Ţ	[	I	
	:		; !	(   		:	:	 
	<u>†</u>	i	i	!	†	†	†	1
		ļ			†		ļ	
	<del>†</del>	l	¦		<del> </del>	<del> </del>	†	1
		ļ			<del></del>	<u> </u>	ļ	
	1000	1075	1000		0	i		
	1060	10/5	1090	0	U		0	

## Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.