Finishing

Leather Goods

RECIPE NO. CLIENT **MEMA 23043**

N°1 DANDELION ARTICLE BASED ON WE RECIPE NO.

11 July 2023 MATERIAL Half calf DATE

COLOUR TPX 13-0758 **TECHNICIAN** Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Cryl 5037/N	100	!	 	 	! !	!	1) 1X ROLLER 20B - 32 g/sqft
Water	200	† !		i	50	† !	REST OVER NIGHT - VACUUM
EUDERM® Driver PE-C	100						BUFFING PAPER 400
Euderm®X- Grade MP-2		850	ļ		 	i 	2) 1X ROLLER 21G - 10gr.sqft
Baygen®Compact LV-2		100					SANDBLAST 120°C - 40 atm
RODA®Pure Luster 1430		50					BUFFING PAPER 800
RODA®Link 5777		10	30				
RODA®Lite 07 MIX		15	100				3) 2X ROLLER 30X
							SANDBLAST 80°C - 40 atm
BAYGEN® Compact LV 2			500				+2X ROLLER 30X
RODA® Base WH 0303/N			500	<u> </u>			
RODA® Pure Luster 1505			50	<u> </u>			4) TIP by ROLLER "Fiamma" by Colibri
Aquaderm®Fluid H			10			10	
							5) 2X SPRAY
RODA® Lac 1028				1000	250		
SELLA® Derm M2 Mix				60	 		6) 2X ROLLER 30X
RODA® PoliperI Gold M			i	<u> </u>	8	i	
Methoxypropanol			 	<u> </u>	250	! !	
RODA® Pur 5805/N3						900	
RODA® Pur W 5814/N Dull]	Ī		100	
RODA® Link PAX			<u> </u>	<u> </u>		10	
RODA® Feel Microsil				ļ		10	
		<u> </u> 	<u> </u>	<u> </u>		<u> </u> 	
				<u> </u>	 	 	
					: 	 	
							<u> </u>
				<u> </u>	 		
							i
Total	400	1025	1190	1060	558	1030	

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.