Finishing

Shoe Upper

CLIENT TFL RECIPE NO. **MEMA 23044**

N°2 TANGERINE ARTICLE BASED ON WE RECIPE NO.

13 July 2023 MATERIAL Half calf DATE

COLOUR TPX 17-1463 **TECHNICIAN** Maurizio Menichetti

Product	1	2	3	4	5	6	Procedure
RODA® Cryl 5037/N	100	i !	ļ		ļ	i !	1) 1X ROLLER 20B - 28 g/sqft
Water	200					 	REST OVER NIGHT - VACUUM
EUDERM® Driver PE-C	100						BUFFING PAPER 400
RODA® Car B 35		500	ļ		ļ		2) 2X ROLLER 30X
BAYGEN® Compact LV 2		100				i !	SANDBLAST 80°C - 40 atm
RODA® Lite 07 Mix AQUADERM® XL 71		100 10	ļ				+ 2X ROLLER 30X
AQUADERINI* XL/1		10				 	3) 2X ROLLER 30X
RODA®Pur 5805/N3			600			; !	
AQUADERM®Matt HPM-N			400		ļ		
RODA®Wax SCH/N			50				
RODA® Pure Luster 1505			30				
Aquaderm®Fluid H		[10			[
]			i i	
	<u> </u>	!	İ			!	
		; !	i		i	i !	
			 			¦	
		<u></u>	<u> </u>			<u> </u>	
						!	
			ļ		ļ	ļ	
		<u>i</u> I	 	<u> </u>	ļ	i I	
		ļ	 		ļ	ļ	
	<u>-</u>	! !	 		ļ	! !	.
		ļ	ļ		ļ		
		i			ļ	i	
		ļ 	ļ		ļ	i 	
		i 	ļ		ļ	İ	
Total	400	710	1090	0	0	0	
Comments:				-		_	1

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.