Finishing

CLIENT



RECIPE NO. BU 6039

ARTICLE N°20 GOLDEN BASED ON WE RECIPE NO.

MATERIAL Cow Calf F.G. DATE July 23

COLOUR TPX 13-0939 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Lite 07 MIX	50		30	i !	i !	i !	i I
EUDERM®Prebottom RP-N -C	100						STAKING BEFORE FINISHING
WATER	300	100	400	150	900		!
RODA® Base AF-B/N	100		250	T			1) 2X/3X SPRAY
ISODERM LA 300	<u> </u>	200		<u> </u>			
RODA® Bind TLC 385			50				2) 1X SPRAY
Aquaderm®XL 71			7	7			IRON 100°C
BAYDERM® Bottom 10 UD			50				DRY MILL OVER NIGHT
RODA® Fix 5090			<u> </u>	100	<u> </u>	<u> </u>	TOGGLE 40°C
RODA® Pure Finish 6271/B			i 	100	i 	<u> </u>	
RODA® Pur 5008			10	20	ļ	<u> </u>	3) 3X SPRAY
RODA® Link 4009			10	20	 		
RODA® Feel N4			<u> </u>	15	100		4) 2X SPRAY
				ļ		ļ	IRON 100°C
				ļ	ļ	ļ	DRY MILL 8hrs
				ļ		ļ	
	- <u>İ</u>		ļ	<u> </u>	ļ	<u> </u>	5) APPLY IN MILLING DRUM IN 2h
				ļ			
	-ļ		ļ	ļ	ļ	ļ	
			i 	ļ	ļ 		i
			!	<u> </u>	! !	<u> </u>	I I
				<u> </u>			
	- <u>i</u>		i 	i 	i 	i 	i
				ļ			-
			! !	<u> </u>	! !	! !	
			ļ	<u> </u>	ļ		
	- <u>İ</u>		<u>i</u>	<u> </u>	<u>i</u>	<u>.</u>	i
				ļ			
			<u>:</u>	!	<u>:</u>	i	
			i 	<u> </u>	i 		
		L	<u> </u>	<u> </u>	ļ	<u> </u>]
			i :	<u>i</u>	i :	i :	
				 		<u></u>	i
	- <u>-</u>		!	<u> </u>	!	<u> </u>	
Total	550	300	807	412	1000	0	
Comments:							•

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.