## Finishing Shoe Upper



51100 0	ppci							
CLIENT	TFL				RECIPE	NO.		BU 6038
ARTICLE N°9 LEMONADE BAS						ASED ON WE RECIPE NO.		
MATERIAL SHEEP SKIN				DATE July 23				
COLOUR	TECHNICIAN						Borgia Roberto	
Product		1	2	3	4	5	6	Procedure
RODA® Lite 07 M	MIX	100						
RODA <sup>®</sup> Pur ADX		50		50				1) 2X ROLLER G25G
WATER			200		100			
RODA <sup>®</sup> Ground	UP-XS	200						2) 1X SPRAY
EUDERM®Preb	ottom RP-N-C	650						EMBOSS ROTOGRAIN 90°C - 50Kg
ISODERM LA 30	00		100				1	
RODA <sup>®</sup> Wax 40				250				3) 3X TIPPING ROLLER 48L
RODA <sup>®</sup> Cor HTP	PMIX			20				REST OVER NIGHT - IRON 120°C - 30 Kg
SELLA® Derm M	12 MIX			5				
RODA <sup>®</sup> Poliparl	Iride Yellow			10			Ī	4) 2X SPRAY
RODA <sup>®</sup> Pur 518	8/N Gloss			100	70			DRY MILL OVER NIGHT
AQUADERM® F	inish HAT				30			KISS PLATE 110°C
RODA <sup>®</sup> Link PA	X				5			
RODA <sup>®</sup> Pur 500	8				20		<u>.</u>	
RODA® Link 400	)9				20		<u>+</u>	
RODA <sup>®</sup> Feel Mi					5			- 4
RODA <sup>®</sup> Wax KC					20			
							1	
							<u>i</u>	
						,		
								1
							<u>i</u>	
							<u>i</u>	
				i 				
				i 				
							<u></u>	
		ļ			Ļ		<u> </u>	
					ļ		L	
							-	
Total		1000	300	435	270	0	0	
Comments:		1000			_/0	<b>J</b>	v	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.