

# Wet-End

## Leather Goods



ARTICLE	SHEEP GLOVE NAPPA (LOW BPS/F)	CLIENT	TFL ITALY (SS 25)
MATERIAL	SHEEP WET BLUE - IMPORTED	RECIPE NO.	N° 19 YELLOW
QUANTITY	30 Skins	DATE	11 August 2023
% based on weight:	shaved weight substance 0.8-0.9 mm	COLOUR	TPX 15-1046
	15 kg	TECHNICIAN	ACI Ranipet

Process	%	kg	Product	Time	Comments
WETBACK回水	100		Water 35°C 水		
Drain控水	0,5		PELTEC® AD-N	30'	Check for proper wetback
Drain控水	200		Water 35°C 水	10'	
DEGREASING -1 脱脂1	1,5		Dryfloat无浴 BORRON® SE		
	0,5		OROPON® WB-I		
	0,2		PELTEC® AD-N	40'	
Drain控水	200		Water 50°C 水		
	0,2		PELTEC® AD-N	20'	Check for proper degreasing
Drain控水	200		Water 35°C 水	10'	
DEGREASING -2 脱脂2	1,5		Dryfloat 无浴 BORRON® SE		
	0,5		OROPON® WB-I		
	0,2		PELTEC® AD-N	40'	
	200		Water 50°C 水		
	2		oxilic acid草酸		
Drain控水	0,2		PELTEC® AD-N	30'	Check for proper degreasing
Drain控水	200		Water 35°C 水		
	2		Salt 盐	30'	
Drain控水	200		Water 35°C 水	10'	
RE-CHROME 铬复鞣	100		Water 35°C 水		
	3		LEVOTAN® RP	30'	
	1,5		SELLATAN® CF-I LIQ	30'	Check ph:3.0-3.2 in BCG to Yellow
	4		Chrome powder 铬粉		
	3		TANIGAN® MBO LIQ		
	0,5		CORIPOL® GLH	45'	
BASIFICATION 提碱	4		BLANCOROL® RC		
	2		SELLASOL® Pure M		
	0,5		CORIPOL® GLH	75'	Check ph:3.8-4.0 in BCG to Green
	1		LEVOTAN® C-C01	40'	Automatic over night next day run for 1 自动过夜

Continuation on Next page

Comments:

BORRON®, CORIPOL®, CROMENO®, DRYWALK®, INVADERM®, MAGNOPAL®, OROPON®, SELLA®, SELLASET®, SELLASOL®, SELLATAN®, and TANNESCO® are registered or filed trademarks, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.