Finishing

CLIENT

ARTICLE



TFL

RECIPE NO. BU 6259

N°16 CREMA BASED ON WE RECIPE NO.

MATERIAL COW CALF DATE July 24

COLOUR TPX 15-3817 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Lite MIX	100	50		 			!
RODA® Pur 5101/N	900			L			1) 2X/3X SPRAY
Water		500	200	500	200		:
EUDERM® Wax CL-C		50		50			2) 2X SPRAY
RODA® Bind 1430		50		50			SANDBLAST 90°C - 50Kg
RODA® Cryl NP 87		50		50			+ 2X SPRAY
RODA® Base AF-B/N		250		100			
AQUADERM® XL 71				10	15		3) 1X SPRAY
RODA® Fix 1000					200		SANDBLAST 90°C - 50Kg
RODA® Fix 5188/N Gloss				 	100		DRY MILL OVER NIGHT - STAKING
RODA® Wax KCF 699					50		
RODA® Tec AW					20		3) 2X SPRAY
RODA® Feel N4				10			
RODA® Lac 103 Dull			100				4) 2X SPRAY
							IRON 90°C - 50Kg
							DRY MILL TO EFFECT
				: 			
				i 			i
				ļ			
				<u> </u>			İ
				i 			i
				L			
				ļ			
				ļ			
							i
Total	1000	950	300	770	585	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.