## **Finishing**

CLIENT

ARTICLE

COLOUR

## **Shoe Upper**

TFL

N°17 ACQUA

BU 6261 RECIPE NO.

BASED ON WE RECIPE NO.

MATERIAL COW SIDE C.G. DATE August 24 **TECHNICIAN TPX 12-0313 Borgia Roberto** 

Product	1	2	3	4	5	6	Procedure
EUDERM® Driver PE-C	100	50		L			
EUDERM® Prebottom VE-N	100	† !		L			1) 1X ROLLER G25G - 30gr.sqft
WATER	200	650					REST OVER NIGHT - VACUUM 60°C - 3"
PRIMAL™ FGR	T	300					REBUFF 400 PAPER
RODA® Lite 07 MIX			150				
Product BC 5288	·	! !	650	650			2) 1X ROLLER G25G 18g/Sf
RODA® Link PAX	T	† !	30	30	20		REST OVER NIGHT - VACUUM 60°C
RODA® Cryl 5416		i	100	100			BUFFED 400 PAPER
PRIMAL™ SCL-371			100	100			
EUDERM® Nappa Soft S-C			50	50	10		3) 2X ROLLER G25G
RODA® Fix 5040 Dull		Ī			300		IRON 90°C - 100Kg
RODA® Fix 5188/N Gloss	Ĭ	i			500		+ 2X ROLLER G25G
AQUADERM® Fluid H	1	<u> </u>	10	10	10		
RODA® Polipearl Iride Green				40			4) 1X ROLLER G 25G
							5) 2X ROLLER 30C
		<u> </u>					
		<u> </u>					
		ļ					
		ļ					
		ļ					
		ļ					
		ļ 					
		ļ					
		ļ					
	ļ	ļ					
		ļ					
	-i	ļ					
		ļ					
	. <del> </del>	<u> </u>		ļ	ļi		i
	ļ	ļ					
	-	ļ			ļi		
	- <del> </del>	<del></del>					
		ļ					
Total	400	1000	1090	980	840	0	
la							<u> </u>

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

