Finishing

CLIENT



RECIPE NO. BU 6249

ARTICLE N°24 BOTTIGLIA BASED ON WE RECIPE N

MATERIAL COW SPLIT DATE June 24

COLOUR TPX 15-0309 TECHNICIAN Borgia Roberto

Product	1	2	3	4	5	6	Procedure
RODA® Line AS	600	900					1) 1X HEAVY SPRAY
EUDERM® Nappa Soft S-C	100						REST FEW HRS
PRIMAL® SB100	150						SANDBLAST 90°C - 30Kg
RODA® Lite 07 MIX	50	100	100	100			
WATER	300	100			300		2) ADHESION
EUDERM® Matt SN-C	100						1X SPRAY 8gr.sqft
AQUADERM® Fluid H	1	10	10	10			
ACRYSOL® RM 819W	1	Х	Х	Х			3) SKIN
AQUADERM® XL50		50			20		1X ROLLER 3gr.sqft
RODA® Line IC	İ		900				
EUDERM® X-GRADE SF/N	Ì		100				4) PRESKIN
RODA® Line SLG	i i			900			1X ROLLER 3gr.sqft
RODA® Pur 5427/N	Ī				100		
ISODERM® LA 83-N-C					100		5) 1X SPRAY
RODA® Feel Microsil					10		VACUUM 60°C - 15"
RODA® Wax KCF 699	I				20		
	1						
	Ī						
	i .						
	I						
	I						
	<u> </u>						
	4555	44	44	40			
Total	1300	1160	1110	1010	550	0	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.