
Finishing

Shoe Upper



Product	1	2	3	4	5	6	Procedure
RODA® Wax 1423	100						
EUDERM® Driver PE-C	50	200	50				CRUST MILLING - 3 HRS
I.P.A.	50						1) 2 X SPRAY
WATER	50	600	600	500			SATILUX AT 120C
RODA® Pur ADX		200					1
RODA® Pure Luster 1430			50				2) 1 X SPRAY
RODA® Pure Luster 1505			50				
RODA® Cryl 114			100				3) 4 X SPRAY
BAYDERM® Bottom 10-UD			100				
SELLA® DERM M2 Mix			10				4) 3 X SPRAY
RODA® Lite 07 Mix			10				IRON @ 120°C - 20Kg
RODA® Wax KCF 699			50	50		[MILLING - 30 MIN
RODA® Fix 1051/N			50	200			IRON @ 120°C - 20Kg
RODA® Fix 5010 Gloss				200			
RODA® Feel N4				10			
RODA® Link PAX				20			
					<u> </u>		
					[
		[[
		Ĺ	<u> </u>	[<u> </u>	Ĺ	
		[[[
		<u> </u>	<u> </u>	<u>[</u>	<u> </u>	<u> </u>	
		<u> </u>		<u>[</u>		<u> </u>	
		<u> </u>					
				ļ		ļ	
Total	250	1000	1070	980	0	0	
Comments	250	1000	10/0	300	U	U	

Comments:

RODA® is a registered or filed trademark, owned by or licensed to TFL in most countries.

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purpose. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility.

We guarantee the satisfactory quality of our products subject to our general terms of sale and delivery.

