

Wet End - Process Formulation (RETAN)



N1 RENOIR wet end.xlsx

Date:

23-Jul-2024

Technician:

ROMANO GIUSEPPE

Company: FASHION S/S 2026

Type of Leather: Shoe Upper & Leather Goods

Aim of Trial: N1 RENOIR

Trial - N°:

2

Color:

Piece count:

25

Project - N°:

Substance:

Material: NEW ZEALAND CALF 新西兰小牛皮

Weight:

% refer to: DRY WEIGHT 干重

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		150,00	0,000	Water水	45			
		1,50	0,000	BORRON® SE				
		1,00	0,000	BORRON® Z				
		1,00	0,000	DERMASCAL® S6				
		2,00	0,000	OROPON® WB			60	DRAIN-WASH控水水洗
		0,000						
		100,00	0,000	Water水	40			
		4,00	0,000	SELLASOL® NG gran			30	
		1,00	0,000	CROMENO BF			30	pH=6
		1,50	0,000	CORIPOL® SG				
		1,50	0,000	CORIPOL® GLH			30	
		50,00	0,000	Water水	50			
		3,00	0,000	LEUKOTAN™ 1093 NW			30	
		3,00	0,000	MAGNOPAL® SFT-A			30	
		3,00	0,000	MAGNOPAL® 450			40	
		5,00	0,000	TANNESCO® HN gran			60	
		2,00	0,000	SODIUM ACETATE醋酸钠		2X10+30		
		2,00	0,000	MAGNOPAL® TGR-A			40	DRAIN-WASH控水水洗
		800,00	0,000	Water水	45			
		6,00	0,000	SELLATAN® WL-G				
		6,00	0,000	CORIPOL® DX-1202				
		6,00	0,000	CORIPOL® UFB-A			60	DRAIN-WASH控水水洗
		0,000						
		300,00	0,000	Water水	50			
		6,00	0,000	sodium formate甲酸钠			20	
		3,00	0,000	sodium bicarbonate小苏打			20	pH=6
		6,00	0,000	LEVOTAN® L				
		6,00	0,000	LUBRITAN™ SPE			40	
		16,00	0,000	CORIPOL® AT				
		2,00	0,000	BORRON® SAF-A			30	
		6,00	0,000	CORIPOL® SG				
		6,00	0,000	CORIPOL® MK-A				
		4,00	0,000	CORIPOL® DX-1202				
		10,00	0,000	MAGNOPAL® IPF			60	
		1,00	0,000	INVADERM® LU			5	
		1,30	0,000	SELLA® FAST ORANGE A				
		0,10	0,000	SELLA® FAST RED A				
		0,10	0,000	SELLA® FAST RED 2B				
		0,05	0,000	SELLA® FAST RED RTN			40	
		400,00	0,000	Water水	60			
		3,00	0,000	Formic acid甲酸		3X10+60		DRAIN-WASH控水水洗
		0,000						
		600,00	0,000	Water水	55			
		6,00	0,000	CORIPOL® BZE/N				
		3,00	0,000	CORIPOL® SG				
		6,00	0,000	CORIPOL® DX-1202				
		3,00	0,000	CORIPOL® AT				
		6,00	0,000	MAGNOPAL® IPF			60	
		1,00	0,000	Formic acid甲酸			30	DRAIN-WASH控水水洗

Mechanical Operation:

HORSE UP OVERNIGHT,HANG TO DRY

搭马过夜，挂晾干燥

Process Information:

Running Time:

11 hrs 55 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..