

Wet End - Process Formulation (RETAN)



N16 CREMA wet end.xlsx

Date: 10-Jul-2024
Technician: Tempesti

Company: FASHION S/S 2026

Type of Leather: Shoe Upper & Leather Goods

Trial - N°:

Aim of Trial: N16 CREMA

Color: 15-3817

Project - N°:

Piece count:

Material: Italian calf wb意大利小牛蓝皮

Substance: 0,8-0,9 mm

% refer to: shaved weight削匀重

Weight:

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300,00	0,000	Water水	40°C			
		1,00	0,000	Formic acid甲酸				
		0,50	0,000	BORRON® ADN			30	
drain 控水			0,000					
		100,00	0,000	Water水	40°C			
		2,00	0,000	CORIPOL® FCT			10	
		5,00	0,000	RETINGAN® LFC			20	
		6,00	0,000	TANNESCO® HN gran				
		6,00	0,000	chromosal B			60	
		0,80	0,000	CROMENO® MFN-1			240	automatic自动过夜
drain wash控水水洗								morning pH: 3,8次日
		150,00	0,000	Water水	35°C			
		3,00	0,000	SELLASOL® NG LIQ				
		0,50	0,000	sodium formate甲酸钠			30	
		0,30	0,000	sodium bicarbonate小苏打				
		5,00	0,000	LEVOTAN® L			40	pH: 4,8-5
drain wash控水水洗								
		100,00	0,000	Water水	30°C			
		6,00	0,000	RETINGAN® LFC			30	
		5,00	0,000	LEVOTAN® HPP			20	
		12,00	0,000	TANIGAN® MBO-A LIQ				
		4,00		RETINGAN® R7			20	
		2,00		TANIGAN® SR				
		x		dyestuffs染料			60	
		100,00		Water水	50°C			
		x		Formic acid甲酸			30	
drain wash控水水洗			0,000					
		100,00	0,000	Water水	50°C			
		7,00	0,000	LEVOTAN® HPP				
		6,00	0,000	CORIPOL® SFC				
		3,00	0,000	CORIPOL® Pure LW				
		0,40	0,000	BORRON® SAF-A			60	
		6,00	0,000	LEVOTAN® RP			30	
		0,50	0,000	Formic acid甲酸			30	
drain 控水								

Mechanical Operation:

set out, vacuum dry 90" at 40°C
伸展，真空40°C90秒

Process Information:

Running Time: 11 hrs 50 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.
Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application..