

Wet End - Process Formulation (RETAN)



N19 MARINELLA wet end.xlsx

Date:

Technician:

ROMANO GIUSEPPE

Company: FASHION S/S 2026

Type of Leather: Shoe Upper & Leather Goods

Trial - N°:

Aim of Trial: N19 MARINELLA

Color:

Piece count:

Project - N°:

Substance:

Material: Sheep skin绵羊皮

Weight:

% refer to: SHAVED WEIGHT 削匀重

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		150,00	0,000	Water水	45			
		1,50	0,000	BORRON® SE				
		1,00	0,000	BORRON® Z				
		1,00	0,000	DERMASCAL® F			60	drain wash控水水洗
			0,000					
		100,00	0,000	Water水	40			
		1,50	0,000	BORRON® NF powder			20	
		0,50	0,000	CORIPOL® SG			30	
		0,50	0,000	Formic acid甲酸			15	pH=3,2
		6,00	0,000	TANNESCO® CPR			60	
		6,00	0,000	TANNESCO® HN gran			60	
		4,00	0,000	TANNESCO® FC			120	AUTOMATIC ON自动过夜
			0,000					IN THE MORNING次日
			0,000					Drain控水
		150,00	0,000	Water水	40			
		2,00	0,000	CROMENO® BF			30	
		0,60	0,000	sodium bicarbonate小苏打			30	pH=5,6
		4,00	0,000	RETINGAN® R7			50	drain wash控水水洗
			0,000					
			0,000					
		100,00	0,000	Water水	50			
		4,00	0,000	SELLASOL® NG gran				
		4,00	0,000	SELLASOL® NFN-F gran				
		4,00	0,000	RETINGAN® R12			60	
		4,00	0,000	SELLASOL® PR 01			30	
		2,50	0,000	CORIPOL® DX-1202				
		2,50	0,000	CORIPOL® UFB-A				
		2,00	0,000	CORIPOL® GF New				
		1,00	0,000	CORIPOL® IC-L				
		2,00	0,000	BORRON® SAF-A			60	
		15,00	0,000	TANIGAN® PURE T-A				
		5,00	0,000	BAYTIGAN® AR			40	
		100,00	0,000	Water水	60			
		3,50	0,000	Formic acid甲酸		3X10+60		drain wash控水水洗

Mechanical Operation:

HORSE UP OVERNIGHT,HANG TO DRY

搭马过夜，挂晾干燥

Process Information:

Running Time:

11 hrs 05 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.