## Wet End - Process Formulation (RETAN)



N24 BOTTIGLIA secon	d step wet end.x/sx	Date:	17-Jun-2024
		Technician:	Volterrani
Company:	FASHION S/S 2026		
Type of Leather:	Shoe Upper & Leather Goods	Trial - N°:	
Aim of Trial:	N24 BOTTIGLIA second step	Color:	15-0309 TPG
		Piece count:	
Project - N°:		Substance:	1,2 mm
Material:	split crust 二层皮坯	Weight:	
% refer to:	dry weight 干重	Drum - N°:	

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1:x)	Time in min	Control
		200,00	0,000	Water水	20°C	(1 . X)	111 1111111	
		1,00	0,000	Ammonia氨水	20 0		15'	add加入
		1,00	0,000	7 trimonia gt/jt			10	add),jjj/ (
		2,00	0,000	SELLASOL® TN				
		2,00	0,000	BAYKANOL® SL				
		5,00	0,000	MAGNOPAL® HS				
		0,30	0,000	SELLASET® Brown H				
		0,30	0,000	SELLA® Fast Olive GN			60'	check penetration 查看渗透
		0,00	0,000	GEEEN T dot GIVE GIV			- 00	add
		400,00	0,000	Water水	50°C			
		3,00	0,000	Formic acid甲酸			30'	drain 控水
						1		
Mechanical O	neration:			<u> </u>	Proce	ss Informa	ation:	

wechanical Operation.	Process information.	
Plate		
贴板		
	Running Time:	0 hrs 0 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.

Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.