

Wet End - Process Formulation (RETAN)



N6 ACACIA wet end 2.xlsx

Date:

Technician:

Company: FASHION S/S 2026

Type of Leather: Shoe Upper & Leather Goods

Trial - N°:

Aim of Trial: N6 ACACIA

Color:

Piece count:

Project - N°:

Substance:

1.2mm

Material: WW MBO MBO鞣制白湿皮

Weight:

% refer to: Shaved weight削匀重

Drum - N°:

Operation	Add	%	Weight in kg	Product	Temp. in °C	Dilution (1 : x)	Time in min	Control
		300,00	0,000	Water水	35			
		0,30	0,000	BORRON® SAF-A			20	pH: 5,0
Drain控水			0,000					
		100,00	0,000	Water水	35			
		3,00	0,000	SELLASOL® NG LIQ				
		1,00	0,000	sodium bicarbonate小苏打			90	pH: 6,1
drain wash控水水洗			0,000					
		50,00	0,000	Water水	30			
		2,00	0,000	CORIPOL® SLG-A		4		
		5,00	0,000	LEVOTAN® AT 01		4	10	
		3,00	0,000	BAYKANOL® PR-A				
	+	10,00	0,000	TANIGAN® MBO-A LIQ		1		
		10,00	0,000	TANIGAN® PURE T-A			30	
		5,00	0,000	CORIPOL® SLG-A		4		
	+	5,00	0,000	LEVOTAN® RP		4	30	
	+	10,00	0,000	TANIGAN® MBO-A LIQ		1		
		10,00	0,000	TANIGAN® PURE T-A				
		10,00	0,000	mimosa WS				
		4,00	0,000	RETINGAN® R7				
	+	2,00	0,000	CORIPOL® SLG-A			180	o/n pH: 4,7
			0,000					
	+	100,00	0,000	Water水	50			
		0,50	0,000	Formic acid甲酸		10	15	
		1,00	0,000	Formic acid甲酸		10	15	
		1,00	0,000	Formic acid甲酸		10	30	pH: 3,7/4,0
drain wash控水水洗			0,000					
		100,00	0,000	Water水	50			
		2,00	0,000	MAGNOPAL® DP			5	
		4,00	0,000	LEVOTAN® L			20	
	+	12,00	0,000	CORIPOL® A				
		1,00	0,000	BORRON® SAF-A				
		4,00	0,000	CORIPOL® GF New		5	60	
	+	1,50	0,000	Formic acid甲酸		10	30	pH: 3,2/3,4
Drain控水			0,000					
		200,00	0,000	Water水	30			
Drain控水			0,000					
drain wash控水水洗								

Mechanical Operation:

set out, vacuum dry 180" at 42°C, hang to dry, stake.

伸展, 真空42°C 180秒, 挂晾干燥, 振软

Process Information:

Running Time:

8 hrs 55 min

Our application recommendations are in line with our present state of knowledge. They do not, however, exempt the customer from performing his own tests to determine the suitability of the supplied products for their intended purposes. Application of the products lies outside the scope of our control and therefore comes within the customer's sphere of responsibility. We guarantee the satisfactory quality of our products subject to general terms of sale and delivery.
Above data are based on the current state of knowledge. However, buyer is not released from his obligation to examine the material on receipt. Seller makes no warranty of merchantability or fitness for practical use or application.